

BITUBOND - 200

Torch applied APP modified bitumen waterproofing membrane
4mm thick reinforced with non-woven polyester mat

DESCRIPTION

Bitubond 200 is an APP and special polymers modified bituminous membrane with additives to perform as a general purpose waterproofing product. The multilayered membrane consists of a spun bonded non-woven polyester core, impregnated and both sides coated with a uniquely formulated polymer modified bituminous compound to meet the best performance at the economic cost.

ADVANTAGES

- Positive barrier to water ingress and dampness
- good tensile strength and tear strength.
- Flexibility at low temperatures
- Good tensile strength and tear resistance
- Accommodates structural movements
- Resistance towards salts and water-borne chemicals.
- Outstanding bonding ability and seam integrity, fast, easy and clean application.

SPECIFICATION

Bitubond 200 waterproofing membrane complies with the requirements of ASTM D 6222 type II, Grade S, UEAtc MOAT 30, DIN 52133 International Standards.

Certificates

The Manufacturing facility is certified with the ISO 9001:2015 QMS, GMP, ISO 14001 E M and ISO 45001 OH & S.

USES

To avoid damp and water leakage risk, it's recommended for:

- Concrete roof and floor slabs
- Basements
- Foundations
- Swimming Pools
- Fountains
- Drain Gutters
- Bathrooms
- Reservoirs
- Bridges
- Tunnels
- Sub-grade Structures
- Car Park Deck Slabs



Technical Data

PROPERTIES	RESULTS	UNIT	TEST METHOD
Length, m	10		ASTM D-5147
Width, m	1		ASTM D-5147
Thickness, mm	4 ± 0.2		ASTM D-5147
Mass per unit area min. (kg/m ²)	4.5 ± 0.2		ASTM D-5147
Softening Point, °C (Ring & Ball)	>155		ASTM D-36
Bottom side coating thickness min. mm	>1.0		ASTM D-5147
Tensile Strength, N/5cm (L/T) at 23 ± 2 °C	850/650		DIN 52123 UEAtc M.O.A.T. 30 ASTM D 5147
Lap Joint Strength, N/5cm (L/T)	850/650		UEAtc M.O.A.T. 30 & 27
Elongation at 23 ± 2 °C (L/T) before and after heat conditioning, at peak load, % minimum	40/40		ASTM D-5147
Tear strength at 23 ± 2 °C N, minimum	450/350		ASTM D-4073 ASTM D-5147
Puncture Resistance, N	700		ASTM E-154
Low temperature flexibility, before and after heat conditioning in °C	0 to -2		ASTM D-5147
Dimensional stability % change, maximum	±0.5		ASTM D-5147
Compound stability, in °C minimum	120		ASTM D-5147
Water absorption, % maximum	3.2		ASTM D-5147
Moisture Content, % maximum	1		ASTM D-5147
Low temperature unrolling, in °C maximum	5		ASTM D-5147
Heat Resistance for 2 hours	No Flow @ 125 °C		UEAtc M.O.A.T. 30 ASTM D 5147

The information given in this data sheets is the average of test of various samples conducted under lab conditions. *In accordance to ASTM and UEAtc Standards results are subjected to 5 to 20% tolerance.



BITUBOND - 200

Torch applied APP modified bitumen waterproofing membrane
4mm thick reinforced with non-woven polyester mat

INSTRUCTION TO USE

SURFACE CLEANING

All surfaces should be smooth, clean and dry. To make sure it is cleaned from nails, grease, dust, debris, oil, protruding elements etc.

PRIMING

Apply one coat of primer and we recommend using Bituprimer. Allow the primer coat to dry until it is tack free. Prior to the application of the membrane, all surfaces must be re-primed if left for more than 24 hours.

APPLICATION

The membrane is unrolled and placed in the correct position. Each roll must side overlap at least 10 cm, while slowly unrolling the membrane the surface is lightly heated by means of a propane gas torch causing surface melting and subsequent adhesion to the surface. End joints should be made with a minimum of 15 cm overlap.

APPLICATION TOOLS AND EQUIPMENT

- Propane gas torch with related gas cylinder
- Knife/cutter
- Trowel with a rounded tip
- Marking Aids
- Measuring Tape
- Fire Extinguisher



HEALTH, SAFETY AND ENVIRONMENT

All safety measures should be observed during application. Fire extinguishers should be available on site. Care should be taken with gas, and torches should not be rested on finished surface or on any materials that can be scratched by flame or hot torch. Gloves and goggles should be worn by all workers during application.

Read, understand and follow all Material Safety Data Sheets and product label information for this product prior to use.

STORAGE

- Keep the products packed in a dry place.
- Keep away from direct sunlight.
- Do not place the pallets on top of each other's.
- Rolls must always be kept in a vertical position.

TECHNICAL SUPPORT

International Insulation Company (IIC) - Bitugulf technical support team consist of expert engineers offers a comprehensive service support to specifiers, end users and contractors, and on-site technical assistance.

NOTE

Various thicknesses are available upon request 3,5,6 mm.

INTERNATIONAL INSULATION COMPANY (BITUGULF)

Factory

Western Shuaiba Industrial, Block (3), Building (90),
Opposite of Kuwait Steel Co.

Telephone: (+965) 23262824 (Factory)

(+965) 90019846 / 90019917 / 96600332 (Sales)

Email: info@bitugulf.net

Showroom

Shuwaikh Industrial, Block (A), Building (139),
Opposite to Hyundai Maintenance Center

Telephone: (+965) 24912765 / 94122711

Email: showroom@bitugulf.net

Note: The technical data provided reflects typical properties based on laboratory tests and practical experience, subject to UEAtc tolerance levels. While we cannot guarantee performance under all conditions, further details are available upon request, with a standard variation of up to 20%

